







RANDOM PACKINGS
GRAPHITE RASCHIG RINGS



FEATURES & APPLICATIONS

When process conditions combine both corrosion and temperature, material selection becomes a key criteria of random packing. For more than 120 years, Mersen has developed advanced materials such as graphite to provide raschig rings capable of handling your severe processes.

Graphilor®, Mersen's isostatic graphite, is the superior mechanical and corrosion resistant graphite in the Chemical markets.


MERSEN GRAPHITE RASCHIG RINGS SPECIAL FEATURES

- they withstand high temperatures (max 200°),
- they resist thermal shocks
- they are perfectly resistant to almost all corrosive agents used in industry (particularly those attacking silico-aluminum materials; hydrofluoric acid, boiling hydrochloric acid, etc.)
- they can be moistened by any liquid and guarantee maximum efficiency for the operation planned.

PRODUCT APPLICATIONS

- HCl separation for production and for HCl recovery
- MCA distillation
- Concentration of hydrofluoric acid
- Separation of chlorophenols


Mersen designs and manufactures process equipment notably columns and their internals (demisters, spargers, distributors, support grids, thermowell, distribution tubes) made of tantalum, graphite, PTFE lined. References are available upon request.



TECHNICAL CHARACTERISTICS

Raschig rings increase the surface area for contact between a liquid and a gas in order to optimize the absorption of the gas in the liquid within the distillation column.

Raschig rings are fragments of tubes made of unimpregnated graphite or amorphous carbon **(A)**. They are placed in large quantities in the column in one or more vessels **(B)** and are supported by graphite grids **(C)**, which enable the liquid to flow towards the next vessel.



Raschig rings are packed in 200l barrels and are marketed in various diameters (mm).

Nominal Size (")	Dimensions OD/ IDxL (mm)	Bulk Density (kg/m ³)	Bulk number (pc/m ³)	Specific surface (m ² /m ³)	Void volume (%)	Packing Factor F (m ⁻¹)
¾ "	18/11x18	700	130 800	259	62	1 070
1 "	25/16x25	660	48 800	187	65	700
1 " ¼	32/22x32	590	23 200	146	68	460
1 " ½	37/25x37	600	15 000	126	67	410
	51/38x51	500	5 750	92	73	230
	86/60x86	570	1 200	54	69	160

Polybloc®, Graphilor® and Boostec® are registered trademarks of Mersen SAS

The specification or data herein contained are only given for indication, without any undertakings whatsoever. Their publication does not suggest the matter is free of any rights whatsoever. Furthermore, due to constant evolution of techniques and norms, we reserve the right to modify, at any time, the characteristics and specifications contained in this document. MERSEN refuses all and any responsibility concerning their use whatever the purpose or application. Any copy, reproduction or information herein contained, in whole or in part, made without MERSEN written consent, is forbidden according to the laws of France and particularly the law nr. 92-597 of July 1st 1992 relating to the copyright.



GLOBAL EXPERT IN ELECTRICAL
POWER AND ADVANCED MATERIALS

EUROPE

FRANCE
Mersen France Py S.A.S.
Tel : +33 (0)3 83 81 60 81
info.pagny@mersen.com

GERMANY
Mersen Deutschland
Linsengericht GmbH
Tel : +49 (0) 6051 71 037
info.lsg@mersen.com

ITALIA
Mersen Italia S.p.A.
Tel : +39 02 82 681 31
ace.italia@mersen.com

SPAIN
Mersen Iberica fma, S.A.
Tel : +34 93 685 7800
contact.iberica@mersen.com

THE NETHERLANDS
Mersen Benelux B.V.
Tel : +31(0)10 298 30 30
contact.schiedam@mersen.com

UNITED KINGDOM
Mersen UK Teesside Ltd.
Tel : +44 (0)1642 790100
ace.uk@mersen.com

RUSSIA & EASTERN EUROPE

Tel : +7 (964) 768 14 05
info.pagny@mersen.com

TURKEY
Mersen Istanbul San. Ür. A. Ş.
Tel : +90 262 751 0262
sales.istanbul@mersen.com

ASIA

CHINA
Mersen XIANDA
Tel : +86 21 5752 7777
info.xianda@mersen.com

INDIA
Mersen India
Tel : +91 9845331292
/+91 9840078844
sales.ace.india@mersen.com

JAPAN
MERSEN FMA JAPAN K.K.
Tel : +81 (3) 5368-3250
ace.japan@mersen.com

KOREA
Mersen Korea Co., Ltd.
Tel : +82 (0)2 598 0071
sales.korea@mersen.com

SOUTH EAST ASIA
Tel : +91 9500041487
graphite.sales@framet.com

NORTH AMERICA

USA
Mersen USA Salem
Tel : +1 540 389-7535
sales.salem@mersen.com

Mersen USA Gonzales
Tel : +1 225 647-6752
graphiterepairs.gonzales@mersen.com

AFRICA

MOROCCO
Mersen Maroc S.A.R.L.
Tel : + 212 (0) 523 38 30 12
contact.maroc@mersen.com

SOUTH AFRICA
Mersen South Africa, (Pty) Ltd.
Tel : +27 011 474 0000
marketing.za@mersen.com

MIDDLE EAST & AFRICA

Tel : +33 (0)3 83 81 60 81
Info.pagny@mersen.com

SOUTH AMERICA

ARGENTINA
Mersen Argentina, S.A.
Tel : +54 11 49 18 21 21
infos.latam@mersen.com

BRAZIL
Mersen Do Brasil, Ltda.
Tel : +55 (11) 4529 1160
vendas.ace.brasil@mersen.com

CHILE
Mersen Chile
Tel : +56 22 621 5680
ventas.chile@mersen.com

COLOMBIA
Mersen Colombia
Tel : +57 (1) 3684588
ace.latam@mersen.com

MEXICO & LATIN AMERICA
Mersen Mexico Monterrey
Tel : +52 (81) 8127 2812
ace.latam@mersen.com

